



NEW

TECHNICAL DATA

Divinycell PA60

LOW DENSITY PET SANDWICH CORE IDEAL FOR A WIDE RANGE OF APPLICATIONS

Divinycell PA60 is a fully recyclable, cost-effective solution for structural sandwich composites applications in the automotive, mobility transportation, industrial and construction markets. Divinycell PA60 has high shear elongation and good ductility that makes it an excellent foam core for thermoforming and compression

molding process, as well as for standard press bonding operations. As a welded PET foam, PA60 has soft weld lines, which enables a high level of aesthetic surface of the finished sandwich parts in automotive and other interior applications.

MECHANICAL PROPERTIES DIVINYCELL® PA60

Property	Test Procedure ¹	Unit		PA60
Compressive Strength ²	ASTM D 1621	MPa	Nominal	0.67
			Minimum	0.51
Compressive Modulus ²	ASTM D1621-B-73	MPa	Nominal	64
			Minimum	47
Tensile strength ²	ASTM D 1623	MPa	Nominal	1.78
			Minimum	1
Tensile modulus ²	ASTM D 1623	MPa	Nominal	78
			Minimum	40
Shear Strength ³	ISO 1922	MPa	Nominal	0.55
			Minimum	0.33
Shear Modulus ³	ISO 1922	MPa	Nominal	13
			Minimum	9
Shear elongation ³	ISO 1922	%	Nominal	40
Shear Strength ⁴	ISO 1922	MPa	Nominal	0.54
			Minimum	0.32
Shear Modulus ⁴	ISO 1922	MPa	Nominal	11
			Minimum	6.5
Shear elongation ⁴	ISO 1922	%	Nominal	42
			Nominal	70
			Maximum	75
Density	ISO 845	kg/m ³	Maximum	75
			Minimum	65
			Nominal	70

1. All values measured at +23°C. Testing is done on foam with welding lines.

2. Properties measured perpendicular to the plane

3. Properties measured parallel to the welding lines, 1-3 direction

4. Properties measured perpendicular to welding lines, 2-3 direction

Nominal value is an average value of a mechanical property at a nominal density.

Minimum value is a minimum guaranteed mechanical property a material has independently of density.

PRODUCT CHARACTERISTICS

- Recyclable
- Excellent ductility and thermoformability
- Good thermal insulation
- Superior aesthetic surface of the finished sandwich parts of automotive interior
- Good chemical resistance
- Resistance to high processing temperature
- Suitable for a variety of processes
- Compatible with most resins used in the composite industry



TECHNICAL CHARACTERISTICS

TECHNICAL CHARACTERISTICS DIVINYCELL® PA60

Characteristics ¹	Unit	PA60	Test method
Density variation	%	± 5	-
Thermal conductivity ²	W/(m·K)	TBD	ASTM C518

1. Typical values are approximate
2. Thermal conductivity measured at +10°C

Maximum processing temperature is dependent on time, pressure and process conditions. Therefore users are advised to contact Diab Technical Services to confirm that Divinycell PA is compatible with their particular processing parameters.

OTHER CHARACTERISTICS DIVINYCELL® PA60

Format		Unit	PA60
Plain sheets	Length	mm	2440
	Width	mm	1220
	Thickness	mm	3-70
GS sheet	Length	mm	1220
	Width	mm	1220
	Thickness	mm	5-50

Other dimensions are available on request.

STORAGE OF PRODUCT

The shelf life of Divinycell is unlimited when it is stored in its original package on ambient indoor storage conditions and protected against UV exposure.

Disclaimer:

This data sheet may be subject to revision and changes due to development and changes of the material. The data is derived from tests and experience. If not stated as minimum values, the data is average data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect of the material or its use. The company reserves the right to release new data sheets in replacement.

All content in this publication is protected by international copyright laws. Copyright © Diab February 2024.

Diab Group

Drottninggatan 7, 5th floor
SE-252 21 Helsingborg, Sweden
Tel +46 (0) 430 163 00
E-mail: info@diabgroup.com